



Technical Specification - KRIEBCOAT Light Bulk - bluish - Volume 1,2 fach - KCLB

| | |
|-------------------------------------|---|
| Raw Material : | 100 % secondary fibre |
| | no chloric bleach in the production process |
| applications: | web offset coldset |
| Age Resistance (DIN 6738-92) | group LDK 12 - 80 = several 100 years |

| | | | | | | | |
|-----------------------|------------------------|----------------|-----------|--|-------------|-----------|--|
| | | | | | | | |
| Basis Weight | g/m² | | 48 | | | 51 | |
| | | | | | | | |
| Basis Weight | g/m ² | DIN EN ISO 534 | 48 ± 2,5% | | | 51 ± 2,5% | |
| | | | | | | | |
| Volume | cm ³ /g | | | | 1,20 ± 0,10 | | |
| | | | | | | | |
| Roughness Bekk FS | sec | DIN 53107 | | | 50 ± 10 | | |
| | | | | | | | |
| Opacity | % | DIN 53.164 | ≥ 92 | | | ≥ 93 | |
| | | | | | | | |
| Brightness | % | ISO 2470 | | | 81 ± 3 | | |
| | | | | | | | |
| Moisture Content abs. | % | EN 20287 | | | 5,00 ± 0,50 | | |
| | | | | | | | |

(Stand: 09.07.2010)



KÜBLER & NIETHAMMER
PAPIERFABRIK KRIEBSTEIN AG

Kübler & Niethammer Papierfabrik Kriebstein AG
Bauhofstraße 1 - 09648 Kriebstein/Sa.

FON: +49 (0) 34 327 97-809 FAX: +49 (0) 34 327 97-934
E-Mail: info@k-n-paper.de www.k-n-paper.de