



**Technical Specification - KRIEBCOAT Light Coldset - bluish - Volume 1,2 fach - KCLC**

<b>Raw Material :</b>	100 % secondary fibre
	no chloric bleach in the production process
<b>applications:</b>	web offset coldset waterless
<b>Age Resistance (DIN 6738-92)</b>	group LDK 12 - 80 = several 100 years

<b>Basis Weight</b>	<b>g/m<sup>2</sup></b>		<b>48</b>		<b>51</b>		
Basis Weight	g/m <sup>2</sup>	DIN EN ISO 534	48 ± 2,5%		51 ± 2,5%		
Volume	cm <sup>3</sup> /g			1,20 ± 0,10			
Roughness Bekk FS	sec	DIN 53107		50 ± 10			
Opacity	%	DIN 53.164	≥ 92		≥ 93		
Brightness	%	ISO 2470		81 ± 3			
Moisture Content abs.	%	EN 20287		5,00 ± 0,50			

( Stand: 09.07.2010 )



**KÜBLER & NIETHAMMER**  
PAPIERFABRIK KRIEBSTEIN AG

Kübler & Niethammer Papierfabrik Kriebstein AG  
Bauhofstraße 1 - 09648 Kriebstein/Sa.

FON: +49 (0) 34 327 97-809 FAX: +49 (0) 34 327 97-934  
E-Mail: info@k-n-paper.de www.k-n-paper.de