



Technical Specification - KRIEBCOAT Light Xtra - bluish - KCLX

Raw Material :	100 % secondary fibre
	no chloric bleach in the production process
applications:	web offset heatset
Age Resistance (DIN 6738-92)	group LDK 12 - 80 = several 100 years

Basis Weight	g/m²		48	51
Basis Weight	g/m ²	DIN EN ISO 534	48 ± 2,5%	51 ± 2,5%
Volume	cm ³ /g		0,90 ± 0,10	
Roughness Bekk FS	sec	DIN 53107	700 ± 100	
Gloss (Gardner 75°)	%	Tappi 480	35 ± 3	
Opacity	%	DIN 53.164	≥ 91	≥ 92
Brightness	%	ISO 2470	75 ± 1,0	77 ± 1,0
Moisture Content abs.	%	EN 20287	5,0 ± 0,5	

(Stand: 09.07.2010)



KÜBLER & NIETHAMMER
PAPIERFABRIK KRIEBSTEIN AG

Kübler & Niethammer Papierfabrik Kriebstein AG
Bauhofstraße 1 - 09648 Kriebstein/Sa.

FON: +49 (0) 34 327 97-809 FAX: +49 (0) 34 327 97-934
E-Mail: info@k-n-paper.de www.k-n-paper.de



Technical Specification - KRIEBCOAT Light Silk - bluish - KCLS

Raw Material :	100 % secondary fibre
	no chloric bleach in the production process
applications:	web offset heatset
Age Resistance (DIN 6738-92)	group LDK 12 - 80 = several 100 years

Basis Weight	g/m²		48	51
Basis Weight	g/m ²	DIN EN ISO 534	48 ± 2,5%	51 ± 2,5%
Volume	cm ³ /g		1,00 ± 0,10	
Roughness Bekk FS	sec	DIN 53107	300 ± 50	
Gloss (Gardner 75°)	%	Tappi 480	20 ± 2	
Opacity	%	DIN 53.164	≥ 92	≥ 93
Brightness	%	ISO 2470	78 ± 1,0	
Moisture Content abs.	%	EN 20287	5,0 ± 0,5	

(Stand: 09.07.2010)



KÜBLER & NIETHAMMER
PAPIERFABRIK KRIEBSTEIN AG

Kübler & Niethammer Papierfabrik Kriebstein AG
Bauhofstraße 1 - 09648 Kriebstein/Sa.

FON: +49 (0) 34 327 97-809 FAX: +49 (0) 34 327 97-934
E-Mail: info@k-n-paper.de www.k-n-paper.de



Technical Specification - KRIEBCOAT Light Bulk - bluish - Volume 1,2 fach - KCLB

Raw Material :	100 % secondary fibre
	no chloric bleach in the production process
applications:	web offset heatset
Age Resistance (DIN 6738-92)	group LDK 12 - 80 = several 100 years

Basis Weight	g/m²		48			51	
Basis Weight	g/m ²	DIN EN ISO 534	48 ± 2,5%			51 ± 2,5%	
Volume	cm ³ /g				1,20 ± 0,10		
Roughness Bekk FS	sec	DIN 53107			50 ± 10		
Opacity	%	DIN 53.164	≥ 92			≥ 93	
Brightness	%	ISO 2470			81 ± 3		
Moisture Content abs.	%	EN 20287			5,00 ± 0,50		

(Stand: 09.07.2010)



KÜBLER & NIETHAMMER
PAPIERFABRIK KRIEBSTEIN AG

Kübler & Niethammer Papierfabrik Kriebstein AG
Bauhofstraße 1 - 09648 Kriebstein/Sa.

FON: +49 (0) 34 327 97-809 FAX: +49 (0) 34 327 97-934
E-Mail: info@k-n-paper.de www.k-n-paper.de