



**Technical Specification - KRIEBCOAT Superior Coldset - Volume 1,2 fach - KCSC**

<b>Raw Material :</b>	100 % secondary fibre
	no chloric bleach in the production process
<b>applications:</b>	web offset coldset waterless
<b>Age Resistance (DIN 6738-92)</b>	group LDK 12 - 80 = several 100 years

			54	57	60	65	70	80
<b>Basis Weight</b>	<b>g/m<sup>2</sup></b>							
			<b>higher 80 g/m<sup>2</sup> to ask</b>					
Basis Weight	g/m <sup>2</sup>	DIN EN ISO 534	54 ± 2,5%	57 ± 2,5%	60 ± 2,5%	65 ± 2,5%	70 ± 2,5%	80 ± 2,5%
Volume	cm <sup>3</sup> /g		1,20 ± 0,10					
Roughness Bekk FS	sec	DIN 53107	50 ± 10					
Opacity	%	DIN 53.164	≥ 93	≥ 93	> 94	> 95	> 96	> 97
Brightness	%	ISO 2470	81 ± 3					
Moisture Content abs.	%	EN 20287	5,0 ± 0,5					

( Stand: 09.07.2010 )



**KÜBLER & NIETHAMMER**  
PAPIERFABRIK KRIEBSTEIN AG

Kübler & Niethammer Papierfabrik Kriebstein AG  
Bauhofstraße 1 - 09648 Kriebstein/Sa.

FON: +49 (0) 34 327 97-809 FAX: +49 (0) 34 327 97-934  
E-Mail: info@k-n-paper.de www.k-n-paper.de